

TISS Industrial (Tangshan) Co., Ltd.

ADD: Room 4-601, Bldg. 218, Tianyuan Garden, TangShan, China

TEL : +86 315-2213773 FAX:+86 315- 2213773 /2233801

EMAIL: tiss@tissindustries.com

Thermal upgraded DDP

Description		HPI-GREEN 0.075mm		
	Standard	MD	CD	TD
Thickness	mm	0.070-0.080	0.076	
Basis weight	g/m ²	56-72	64.7	
Density	g/cm ³	0.80-0.90	0.85	
Tensile Strength	MPa	MD≥67	128.32	22.35
		CD≥13		
Elongation	%	MD≥2.0	2.5	8.0
		CD≥4.0		
Dielectric Breakdown Strength	kv/mm	Ave.≥8.00	Ave. 9.24	Min. 8.10
		Min.≥6.50		
Moisture Content	%	≤10	7.5	
Ash Content	%	≤0.7	0.238	
Air Permeability	cc/100cc		294	
Nitrogen Content	%		1.94	
Tear Strength	g		55	108
Test Condition Temperature 23 Humidity 50%				